

CLAIM AMENDMENTS

1. (Currently Amended) A powder coating composition comprising:
 - a film-forming resin; and
 - a plurality of particles having an average particle size between ~~0.4~~ 1 and 15 microns dispersed in said resin, wherein the particles have a hardness sufficient to impart greater mar and/or scratch resistance as compared to no particle being present, and wherein the difference between the refractive index of the resin and the refractive index of the particles is less than one.
2. (Withdrawn) The coating of Claim 1, wherein said particles are organic particles.
3. (Withdrawn) The coating of Claim 1, wherein said particles are diamond particles.
4. (Withdrawn) The coating of Claim 6, wherein said inorganic particles are carbide particles selected from titanium carbide and boron carbide.
5. (Withdrawn) The coating of Claim 6, wherein said inorganic particles are silicon carbide particles having a median particle size of less than 3 microns.
6. (Original) The coating of Claim 1, wherein said particles are inorganic.
7. (Withdrawn) The coating composition of Claim 6, wherein said inorganic particles are selected from silica, alkali alumina silicate, borosilicate glass, nitrides, oxides, quartz, nepheline syenite, zircon, buddeluyite, and eudialyte.
8. (Withdrawn) The coating of Claim 7, wherein said silica is crystalline silica, amorphous silica, precipitated silica or mixtures thereof.

9. (Withdrawn) The coating of Claim 7, wherein said nitride is boron nitride, silicon nitride, or mixtures thereof.

10. (Original) The coating of Claim 6, wherein said inorganic particles are uncalcined alumina.

11. (Original) The coating of Claim 6, wherein said inorganic particles are calcined unground alumina having a median crystallite size less than 5.5 microns.

12. (Previously amended) The coating of Claim 6, wherein said inorganic particles are calcined ground alumina having a median particle size of less than 3 microns.

13. (Withdrawn) The coating of Claim 1, wherein said plurality of particles is a mixture of particles.

14. (Canceled)

15. (Original) The coating of Claim 1, wherein the film-forming resin comprises at least one reactive functional group containing polymer and at least one curing agent having functional groups reactive with the functional group of the polymer.

16. (Original) The coating of Claim 15, wherein the polymer is selected from acrylic polymers, polyester polymers, polyurethane polymers, and polyether polymers.

17. (Original) The coating composition of Claim 16, wherein the polymer comprises reactive functional groups selected from epoxy groups, carboxylic acid groups, hydroxyl groups, isocyanate groups, amide groups, carbamate groups, carboxylate groups and mixtures thereof.

18. (Canceled)

19. (Original) The coating of Claim 1, wherein the average particle size ranges between 1 and 10 microns.

20. (Original) The coating of Claim 19, wherein the average particle size ranges between 3 and 6 microns.

21. (Original) The coating of Claim 1, wherein the average particle size is less than 3 microns.

22. (Original) The coating of Claim 1, wherein the average Mohs hardness of the particles is 4.5 or greater.

23. (Original) The coating of Claim 22, wherein the average Mohs hardness is 5 or greater.

24. (Original) The coating of Claim 23, wherein the average Mohs hardness is 8 or greater.

25. (Withdrawn) The coating of Claim 1, wherein the average Mohs hardness is between 4.5 and 7.5.

26. (Original) The coating of Claim 1, wherein said particles are spherical.

27. (Original) The coating of Claim 1, wherein said particles are nonuniform.

28. (Original) The coating of Claim 1, wherein said particles are platy.

29. (Original) The coating of Claim 1, wherein said particles are calcined.

30. (Original) The coating of Claim 1, wherein the weight percent of the particles is between 0.1 and 20.

31. (Original) The coating of Claim 30, wherein the weight percent is between 0.1 and 10.

32. (Original) The coating of Claim 30, wherein the weight percent is between 0.1 and 8.

33. (Currently Amended) The coating of Claim 1, wherein the weight percent of the particles is greater than 5.

34. (Original) A substrate coated with the coating of Claim 1.

35. (Original) The substrate of Claim 34, wherein said substrate is metallic.

36. (Original) The substrate of Claim 34, wherein said substrate is polymeric.

37. (Original) The substrate of Claim 34, wherein one or more additional layers are disposed between the substrate and the coating.

38. (Original) The substrate of Claim 34, wherein the coating is between 0.1 and 10 mils thick.

39. (Original) A method for improving the scratch and/or mar resistance of a substrate comprising applying to at least a portion of the substrate the coating of Claim 1.

40. (Original) The method of Claim 39, wherein an intervening layer is applied to the substrate prior to application of the coating.

41. (Previously Presented) A method for preparing a powder coating comprising the step of extruding together a film-forming resin and a plurality of particles, wherein the particles have a hardness sufficient to impart greater mar and/or scratch resistance to the coating as compared to no particle being present, and wherein the difference between the refractive index of the resin and the refractive index of the particles is less than one.

42. (Currently Amended) A cured powder coating comprising a film-forming resin having a plurality of particles with an average particle size between 1 and 15 microns dispersed therein, wherein the particles have a hardness sufficient to impart greater mar and/or scratch resistance as compared to no particle being present, ~~which wherein the cured powder coating~~ undergoes less than 10 percent gloss reduction after 500 hours of QUV exposure, and wherein the difference between the refractive index of the resin and the refractive index of the particles is less than one.

43. (Original) The coating of Claim 42 having less than 5 percent gloss reduction after 500 hours of QUV exposure.

44. (Original) The coating of Claim 42, wherein the gloss reduction improves after QUV exposure.

45. (Original) The coating of Claim 1, wherein said particles are heat treated prior to being dispersed in said resin.

46-49. (Canceled)

50. (Original) The coating of Claim 1, wherein the average particle size is less than 10 microns.

51. (Previously Presented) A curable powder coating comprising:

a film-forming resin comprising at least one polymer having at least one reactive functional group and at least one curing agent having at least one functional group reactive with the functional group of the polymer; and

alumina particles having an average particle size of less than 3 microns dispersed in said resin in an amount of 0.1 to less than 5 percent by weight.

52. (Previously Presented) The coating of Claim 51, wherein the difference between the refractive index of the resin and the refractive index of the particles is less than one.

53. (Previously Presented) The coating of Claim 6, wherein said inorganic particles are tabular alumina:

continued

54. (Previously Presented) The coating of Claim 6, wherein said inorganic particles are calcined alumina.

55. (Previously Presented) The coating of Claim 53, wherein said alumina has an average particle size less than 3 microns.

56. (Previously Presented) The coating of Claim 54, wherein said alumina has an average particle size less than 3 microns.

57. (Previously Presented) The coating of Claim 55, wherein the weight percent of said alumina is less than 5 weight percent, based upon the weight of the coating.

58. (Previously Presented) The coating of Claim 56, wherein the weight percent of said alumina is less than 5 weight percent, based upon the weight of the coating.

Please add the following new claims:

59. (New) A powder coating composition comprising:
a film-forming resin; and
a plurality of particles having an average particle size between 1 and 15 microns dispersed in said resin, wherein the composition is prepared by extruding together the film-forming resin and the particles, wherein the particles have a hardness sufficient to impart greater mar and/or scratch resistance as compared to no particle being present.
60. (New) The coating composition of claim 59, wherein the particles are alumina particles.
61. (New) The coating composition of Claim 59, wherein the film-forming resin comprises at least one reactive functional group containing polymer and at least one curing agent having functional groups reactive with the functional group of the polymer.
62. (New) The coating composition of Claim 61, wherein the polymer is selected from acrylic polymers, polyester polymers, polyurethane polymers, polyether polymers and mixtures thereof.
63. (New) The coating composition of Claim 61, wherein the polymer comprises reactive functional groups selected from epoxy groups, carboxylic acid groups, hydroxyl groups, isocyanate groups, amide groups, carbamate groups, carboxylate groups and mixtures thereof.